EDXRF1620 - Titanium on Aluminum

Scope

This application note demonstrates the measurement of titanium (Ti) conversion coating on aluminum using NEX QC.

Background

Aluminum and steel are often coated with a protective conversion coating, also called passivate or passivation coating, to prevent oxidation and corrosion of the base metal. Conversion coatings include chromium (Cr), titanium (Ti), vanadium (V), manganese (Mn), nickel (Ni), or zirconium (Zr). A phosphate coating may be applied as well to minimize wear on cutting tools and stamping machines. Aluminum is often coated for use in aircraft parts, aluminum window frames, and other similar industries where the aluminum is exposed to weathering. Steel for the automotive industry is typically first galvanized with a zinc coating before the conversion coating is applied. Protected steel is also used for outdoor sheds and other similar uses where steel is exposed to weathering. Conversion coating also helps in the retention of paint for the final finished product.

Calibration

An empirical calibration was built using a set of standards assayed by careful weigh-strip-weigh.

Element: Ti Units: mg/ft²		
Sample I.D.	Standard value	Calculated value
STD 1	0.06	0.076

STD 2	0.24	0.199
STD 3	0.53	0.573
STD 4	1.16	1.187
STD 5	2.57	2.489
STD 6	4.10	4.137

Correlation plot Ti on aluminum

Recovery and repeatability

To demonstrate repeatability (precision), the three calibration standards were chosen. Each sample was measured in a static position with typical results shown below.

Element: Ti Units: mg/ft²			
Sample I.D.	Standard value	Average value	Std. dev
STD 2	0.24	0.206	0.012
STD 4	1.16	1.190	0.017
STD 6	4.10	4.142	0.023

Conclusion

The performance shown here demonstrates NEX QC provides excellent sensitivity and performance for the measurement of titanium conversion coatings on aluminum.

Related products

NEX QC Series

Combines quality, affordability, and performance for a wide
range of applications